

SPUR+™ 3030 Prepolymer

AMERICAS & ASIA



MARKETING BULLETIN

SILANES - ADHESIVES & SEALANTS ADDITIVES

SPUR+ 3030 prepolymer is an excellent candidate to consider for formulating non-isocyanate, moisture curable roof coatings and waterproof membranes. It was developed to enable the formulation of roof coating with a wide application window and excellent fully cured properties including tear, UV and water resistance.

Key Features and Typical Benefits

- Low viscosity can enable broad formulation latitude
- Proprietary pre-polymer design yields a balance of physical and mechanical properties desirable in a roof coating formulation
- Greater hydrophobicity than conventional hybrid polymers
- Improved heat resistance

Typical Physical Properties

Property	Value
Appearance	Colorless, clear to slightly opaque
Active Content	100%
Specific Gravity at 25 °C	0.9554 gm/cm ³
Viscosity at 25 °C	~2500 cP

Typical properties are average data and are not to be used as or to develop specifications.

Typical Mechanical Properties After Cure

Property	Value
Tensile Strength at Break (psi)	600
Elongation at Break (%)	180
Modulus at 100% Extension (psi)	220
Hardness Shore A	42

Typical properties are average data and are not to be used as or to develop specifications.

The prepolymer was cured via the addition of 1% Fomrez† UL-28 & 0.5% DMDEE in a humidity chamber at 23 °C and 50% relative humidity for ten days, and then tested according to ASTM D412 for tensile properties and ASTM C661 for hardness.

Typical Formulation in Roof Coating

Examples of Roof Coating Formulations

	Formulation 1	Formulation 2	Formulation 3
SPUR+ 3030 prepolymer	44.86	49.25	36.04
Tinuvin† 765	0.76		
Tinuvin 213	0.76		
Tinuvin 384-2		0.99	
Eversorb† 81			1.65
Jayflex† DIDP	7.64		
Acclaim† 8200			5.15
Silquest™ A-137 silane	7.45		8.01
Carbital† C110S	34.5	45.31	
Omyacarb† 3 FL			44.28
DuPont Ti-Pure† R 960	2.86		
Tronox† C828	1.97	4.12	
Silquest A-1100™ silane		0.47	
Silquest A-1120 silane	0.46		0.25
Silquest A-2120 silane	0.46		0.25
Silquest A-Link™ silane	1.58		
Silquest A-171™ silane		0.2	
Fomrez† UL-59	0.25	0.23	0.25
Total	100	100	100
Viscosity of the formulation at 25 °C (cP)	~2000	~7,000	~ 5,000

Product formulations are included as illustrative examples only. Momentive makes no representation or warranty of any kind with respect to any such formulations, including, without limitation, concerning the efficacy or safety of any product manufactured using such formulations.

Physical Properties of the Roof Coatings Formulations

	Formulation 1	Formulation 2	Formulation 3
Tensile Strength at BK (psi)	392	380	544
Elongation at BK (%)	330	266	136
Hardness Shore A	46	55	60
Tear Resistance (lbs/in)	57	58	45

Note: Test data. Actual results may vary.

Weatherability Test of Roof Coating Formulations

The formulated roof coatings were cured in a humidity chamber at 23 °C and 50% relative humidity for seven days, and then tested according to ASTM D412, C661, and D426 for tear resistance.

Roof coating formulation 1 was selected for more extensive testing of weatherability, as it displayed a desirable balance of elongation, hardness and tear resistance and possessed the lowest viscosity.

Weatherability Test Results of Roof Coating Formulation 1

	Tensile Strength at BK (psi)	Elongation (%)	Hardness Shore A
Heat Resistance Test at 80 °C			
Initial	392	330	46
After 1 week	348	242	45
After 3 weeks	319	220	45
QUV-A at 50 °C (ASTM G 53)			
Initial	392	330	46
After 1 week	348	246	43
After 3 weeks	363	275	40
Cold Temperature (-20 to -25 °C)			

The test samples are flexible after storage at -20 °C to -25 °C for four hours.

Note: Test data. Actual results may vary.

Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute the permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

Product Safety, Handling and Storage

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. SDS are available at www.momentive.com or, upon request, from any MPM representative.

For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.



Customer Service Centers

Worldwide Email:
commercial.services@momentive.com

AMERICAS

+1 800 295 2392
Toll free*
+ 704 805 6946
Direct Number

LATIN AMERICA

BRAZIL
+55 11 4534 9650
Direct Number

MEXICO
+52 55 2169 7670
Direct Number

*All American countries

ASIA PACIFIC

CHINA
800 820 0202
Toll free
+86 21 3860 4892
Direct number

JAPAN
+81 3 5544 311
Direct number

KOREA
+82 2 6201 4600
Direct number

EMEA- EUROPE, MIDDLE EAST, AFRICA & INDIA

EUROPE
+ 390510924300
Direct number

INDIA, MIDDLE EAST & AFRICA
+ 91 44 71212207
Direct number*

*All Middle Eastern countries, Africa, India, Pakistan, Bangladesh, Sri Lanka.

SOUTH EAST ASIA, AUSTRALIA & NEW ZEALAND

+60 3 9206 1543
Direct number*

*South East Asia countries (Malaysia, Singapore, Thailand, Indonesia, Vietnam, Philippines, Cambodia, Myanmar / other countries located in Pacific region).

Disclaimer

Each user bears full responsibility for making its own determination as to the suitability of Supplier's materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier's products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier's standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

BEFORE HANDLING ANY PRODUCTS MENTIONED, REVIEW THE LATEST SAFETY DATA SHEET (SDS) AND LABEL FOR PRODUCT SAFETY INFORMATION, SAFE HANDLING INSTRUCTIONS, PERSONAL PROTECTIVE EQUIPMENT IF NECESSARY, EMERGENCY SERVICE CONTACT INFORMATION, AND ANY SPECIAL STORAGE CONDITIONS REQUIRED FOR SAFETY. MOMENTIVE MAINTAINS AN AROUND-THE-CLOCK EMERGENCY SERVICE FOR ITS PRODUCTS. SDS FOR MOMENTIVE PRODUCTS ARE AVAILABLE AT WWW.MOMENTIVE.COM OR, UPON REQUEST, FROM ANY MOMENTIVE REPRESENTATIVE. USE OF OTHER MATERIALS IN CONJUNCTION WITH MOMENTIVE PRODUCTS MAY REQUIRE ADDITIONAL PRECAUTIONS. PLEASE REVIEW AND FOLLOW THE SAFETY INFORMATION PROVIDED BY THE MANUFACTURER OF SUCH OTHER MATERIALS.

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY "SUPPLIER"), ARE SOLD SUBJECT TO SUPPLIER'S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. EXCEPT AS PROVIDED IN SUPPLIER'S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN.

Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier's standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier.

The use of the "™" symbol designates registered or unregistered trademarks of Momentive Performance Materials Inc. or its affiliated companies.

Momentive and the Momentive logo are registered trademarks of Momentive Performance Materials Inc.

Copyright 2022 Momentive Performance Materials Inc. All rights reserved.