

Magnasoft™ CS-1 Textile Softener

Product Description

Magnasoft CS-1 textile softener is a linear silicone copolymer emulsion that can help impart durable softness and slickness, with virtually no fabric yellowing, to a broad range of fabrics, including wool and cashmere, that require a silky and moisturizing hand.

Because of good shear stability at high temperature and alkaline conditions, it is an excellent candidate to consider for use in tough application conditions such as jet finishing and over-flow finishing, in addition to normal exhaustion and pad-bath finishing for fabrics.

Key Features and Typical Benefits

- Slippery, full and in-depth softness as opposed to a greasy hand feel, on virtually all types of fabrics, including wool, cashmere, polyester, polyester blends and acrylic fabrics
- Due to good shear stability at high temperatures up to 80 °C and alkaline conditions (pH 10), applicable in most types of textile finishing process
- Compatible with most organic softeners, durable press resins, optical brightening agents and anti-static agents typically used in the textile finishing bath
- May enhance stretch recovery with a bouncy and drapable effect, including on wool and cashmere
- Ready-to-use: water dispersible and/or water dilutable
- Causes virtually no yellowing of white and light-shade fabrics
- Typically does not affect the shade of dark color fabrics
- Potentially re-dyeable and over-dyeable
- Contains no added alkyl phenol based chemicals

Typical Physical Properties

Appearance	Translucent to hazy emulsion
pH	5.0
Viscosity (#1, 60 rpm, 25 °C), cps	30
Ionic Characteristics	Non-ionic

Typical properties are average data and are not to be used as or to develop specifications.

Potential Applications

Magnasoft CS-1 textile softener can be easily applied with or without pre-dilution, in either exhaustion or padding textile finishing processes. It can be considered for use with virtually all types of fabrics, including wool and cashmere.

The use level of Magnasoft CS-1 textile softener is subject to the softness required, type of fabric and textile finishing process but the typical use level and conditions are as follows:

1. Pad - Dry - Cure Continuous Process for Woolen Woven Goods

Dosage : 20 g/l (light fabric) - 35 g/l (heavy fabric)

pH : 5.0 - 6.0

Temperature : 20 - 30 °C

Pick-up : 65 - 85 %

Drying : 100 - 110 °C

2. Exhaustion Process for Cashmere Knitted Garments

Pre-treatment (lubricants, dirt & grease removal) □ rinsing □ draining □ softening □ draining □ drying

Dosage : 3.0 ~ 5.0 % of the weight of the fabric

Liquor Ratio : 1/8 ~ 1/10

pH : 5.0 ~ 6.0

Temperature : 20 ~ 40 °C

Time : 15 ~ 30 min.

Drying : 100 ~ 120 °C

Precaution During Use

- Ensure that the Magnasoft CS-1 textile softener solution is completely homogenous before use
- Clean the pad bath/exhaustion bath before applying Magnasoft CS-1 textile softener and keep the mangle clean while finishing
- The softness imparted by Magnasoft CS-1 textile softener is maximized 24 hours after treatment due to the complete orientation and relaxation of the silicone polymer, on the fabric treated

Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute the permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

Product Safety, Handling and Storage

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. SDS are available at www.momentive.com or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

Customer Service Centers

For additional information, please contact our Customer Service Team

AMERICAS	+1 800 295 2392 Toll Free* +704 805 6946 Direct Number
LATIN AMERICA	BRAZIL +55 11 4534 9650 Direct Number MEXICO +52 55 2169 7670 Direct Number *All American countries
EMEA – EUROPE, MIDDLE EAST, AFRICA & INDIA	EUROPE +390510924300 Direct Number INDIA, MIDDLE EAST & AFRICA +91 44 71212207 Direct Number* *All Middle Eastern countries, Africa, India, Pakistan, Bangladesh, Sri Lanka
ASIA PACIFIC	CHINA 800 820 0202 Toll Free +86 21 3860 4892 Direct Number JAPAN +81 3 5544 311 Direct Number KOREA +82 2 6201 4600 Direct Number SOUTH EAST ASIA, AUSTRALIA & NEW ZEALAND +60 3 9206 1543 Direct Number* *All East Asia countries (Malaysia, Singapore, Thailand, Indonesia, Vietnam, Philippines, Cambodia, Myanmar / other countries located in Pacific region)
Visit us at www.momentive.com	

DISCLAIMER - THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY "SUPPLIER"), ARE SOLD SUBJECT TO SUPPLIER'S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER'S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBE HEREIN.

Each user bears full responsibility for making its own determination as to the suitability of Supplier's materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier's products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier's standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

The use of the "™" symbol designates registered or unregistered trademarks of Momentive Performance Materials Inc. or its affiliated companies.

Momentive and the Momentive logo are registered trademarks of Momentive Performance Materials Inc.

Copyright 2022 Momentive Performance Materials Inc. All rights reserved.



260 Hudson River Road
Waterford, NY 12188 USA
momentive.com