

SilFORT™ MHC2700 Clearcoat

Product Description

SilFORT MHC2700 Clearcoat is a thermally cured siloxane-based primerless hardcoat system used to protect glossy, matte, and colored anodized aluminum substrates against corrosion, chemicals and scratches. It offers excellent acid and alkali resistance in the range of pH 1.0 to 13.5, while maintaining the desired appearance of the substrate.

This direct-to-metal sol-gel coating system can generally be applied by either spray, dip, or flow coating, allowing for greater design freedom. Curvatures, radii and orifices can typically be managed in the coating process without making any design compromises. For brushed or matte surfaces, the gloss-level can be adjusted according to the desired optical appearance and structure of the surface by the incorporation of Momentive's SilFORT MHC Matte additive.

Key Features and Typical Benefits

- Direct-to-metal / primerless adhesion to anodized aluminum
- Exceptional pH resistance (pH 1.0 to >13.5)
- Excellent corrosion resistance
- Excellent scratch resistance
- Excellent chemical resistance
- Wide application window

Typical Physical Properties

Property ⁽¹⁾	Unit	SilFORT MHC2700 Clearcoat
Physical Form	-	Liquid
Color	-	Milky white
Solids Content	%	Approx. 25
Density (@ 25°C)	g/cm ³	0.93
Kinematic Viscosity (@ 25°C)	cSt	Approx. 5.5
pH	-	Approx. 5
Shelf Life ⁽²⁾	Days	300 (stored below 10°C)

⁽¹⁾ As supplied. Typical properties are average data and are not to be used as or to develop specifications.

⁽²⁾ From date of manufacture.

Potential Applications

- Exterior automotive parts made from anodized aluminum (e.g. window trim, roof rails)
- Interior automotive parts made from anodized aluminum
- Glossy, matte or colored substrates

General Considerations for Use

	SilFORT MHC2700 Clearcoat
Application Method	Spray, flow, dip
Reducing Solvents ⁽³⁾	1-Butanol (CAS# 71-36-3) 2-Propanol (CAS# 67-63-0)
Recommended Coating Thickness ⁽⁴⁾	4 – 6 µm

⁽³⁾ If necessary for application process, other suitable solvents may be considered.

⁽⁴⁾ Other thicknesses can be considered but may affect performance.

SilFORT MHC2700 Clearcoat is a cross-linking product, sensitive to extended exposure to elevated temperature. Storage at lower temperatures (< 0°C) may increase typical shelf-life beyond 10 months.

Once the product has reached ambient temperature it should be used within 7 days. Re-refrigeration to less than 10°C should be considered when product will not be used within 24 hours.

For a particle-free surface, components should be processed in a climate-controlled cleanroom environment that complies with ISO14664-1, equal to or lower than class 6. Before applying any coating, part surface temperature should be <35°C.

For more detailed guidance on the use of SilFORT MHC2700 Clearcoat, please request the accompanying Processing Guide from your local Momentive representative.

Packaging

Products are currently available in:

- 25 kg Steel Pail with PE liner
- Other packaging sizes available upon request

Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute the permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

Product Safety, Handling and Storage

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. SDS are available at www.momentive.com or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

Contact Information

Email

commercial.services@momentive.com

Telephone

Americas

+1 800 295 2392
Toll free*
+704 805 6946
Direct Number

Latin America

Brazil
+55 11 4534 9650
Direct Number

EMEAI- Europe, Middle East, Africa & India

Europe
+390510924300
Direct number

ASIA PACIFIC

China
800 820 0202
Toll free
+86 21 3860 4892
Direct number

*All American
countries

Mexico
+52 55 2169 7670
Direct Number

India, Middle East & Africa
+ 91 44 71212207
Direct number*

Japan
+81 3 5544 3111
Direct number

*All Middle Eastern
countries, Africa, India,
Pakistan, Bangladesh, Sri
Lanka.

Korea
+82 2 6201 4600
Direct number

**South East Asia, Australia & New
Zealand**
+60 3 9206 1543
Direct number*

*South East Asia countries (Malaysia,
Singapore, Thailand, Indonesia,
Vietnam, Philippines, Cambodia,
Myanmar / other countries located in
Pacific region).

For literature and technical assistance, visit our website at: www.momentive.com

DISCLAIMER:

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY "SUPPLIER"), ARE SOLD SUBJECT TO SUPPLIER'S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER'S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of Supplier's materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier's products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier's standard Conditions

of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

The use of the "™" symbol designates registered or unregistered trademarks of Momentive Performance Materials Inc. or its affiliated companies. Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.



260 Hudson River Road Waterford,
NY 12188 USA
momentive.com

Copyright 2023 Momentive Performance Materials Inc. All rights reserved.