

SilGrip™ PSA529 Pressure Sensitive Adhesives

Product Description

SilGrip™ PSA529 silicone pressure sensitive adhesive is a toluene solution of polysiloxane gum and resin. It is supplied at 55 percent silicone solids and may be further diluted with aromatic, aliphatic or chlorinated solvents. PSA529 may be blended with SR545 resin dispersion or with other methyl-based silicone pressure sensitive adhesives to obtain specific performance properties.

PSA529 has an overall balance of peel strength, cohesion, lap shear strength and high temperature holding power, which provides a versatility that makes this product useful in a wide variety of applications, including fastening and bonding of dissimilar materials.

Key Features and Typical Benefits

- Wide temperature range performance, maintains good shear and tack properties at intermittent temperatures up to 500° F
- Adhesion to a wide variety of surfaces (stainless steel, anodized aluminum, steel) including low energy surfaces (silicones, fluoropolymers, polyolefines)
- Resistance to moisture, weathering (ozone, sunlight), chemical (acids, alkalis, oils) and biological (fungus) attack
- Elastomeric properties after curing with SRC18 catalyst
- Creep resistance

Typical Physical Properties

Property	Value
Silicone Solids, %	55
Specific Gravity	0.99
Density, lbs/gal	8.2
Viscosity @ 25° C (77° F), cps (Brookfield RVF, #3 Spindle, 20rpm)	2,500
Color	Light Straw, Translucent
Flash Point, TCC, ° C (° F)	1.6 (35)
Solvent	Toluene

Typical cured adhesive properties

Peel Adhesion (1), grams/inch	2350
Tack (2), g/cm ²	440

1. 2 mil dry adhesive thickness, 2 mil polyester film, uncatalyzed, curing cycle: 10 minutes air dry, 10 minutes at 150° C, stainless steel, 12 inches/minute, 180° C angle.
2. Polyken Tack Tester, 1000g weight, 1second dwell time, cm/second draw speed, 2 mil dry adhesive thickness, 2 mil polyester film, uncatalyzed, curing cycle: 10 minutes air dry, 10 minutes at 150° C.

Processing Recommendations Laminating Applications

PSA529 silicone adhesive is supplied at a viscosity suitable for conventional coating equipment. If necessary, it may be thinned with toluene, xylene or other compatible solvents. After the adhesive is applied to the substrate, it is exposed to a two-step process: solvent removal and curing.

Processing of PSA529 Catalyzed with Benzoyl Peroxide Solvent Removal

To achieve optimum adhesive properties, it is essential to optimize the drying step of the process in order to assure that the solvent is removed from the adhesive film before the curing step of the process starts. Improper drying will result in residual solvent entrapment within the adhesive. If the adhesive is then exposed to temperatures higher than 93.5o C (200o F), decomposing peroxide catalyst can cause crosslinking reaction between solvent and adhesive through methyl groups on siloxane chains and on solvent molecules and adversely affect the properties of the adhesive. Typical temperature range for the drying step of the process is 83o C (180o F) to 90o C (194o F). A typical drying cycle is 2 minutes at 90o C (194o F).

Curing Process

Once the solvent is removed from the adhesive film, the peroxide cure should be initiated by exposure to heat. A typical curing cycle is 2 minutes at 165o C (329o F). Longer exposure time and higher temperature, up to 204o C (400o F), can be used without adverse effects. The exact conditions required to achieve a complete cure will depend on oven length and efficiency, peroxide type and type of substrate used, and should be established during experimental trials on the machine.

Catalysts

High purity, 98% benzoyl peroxide (3) in the quantity of 1 to 3% based on silicone solids, has been found to give the most consistent results in curing of silicone pressure sensitive adhesives. In applications requiring low temperature cure, 2,4-dichlorobenzoyl peroxide, which is activated at 132° C (270° F), can be used. It should be noted that 2,4-dichlorobenzoyl peroxide may generate polychlorinated biphenyls during the curing process. Please refer to Code of Federal Regulations, title 40, part 761 regarding incidental PCB byproducts if 2,4- dichlorobenzoyl peroxide is utilized.

The peroxide should be dispersed in solvent before it is mixed with the adhesive. Thorough mixing of the peroxide and adhesive to achieve homogeneous dispersion is essential for consistency of finished product.

3. Available from: Elf Atochem North America, Inc.

Processing of PSA529 Catalyzed with SRC18

Room temperature curing can be obtained by catalyzing PSA529 adhesive with SRC18 amino functional silane.

Note: It is necessary (for maximum physicals) to add an amount of SRC18 catalyst that will eventually cause complete cure of PSA529 adhesive. Completely cured PSA529 adhesive is tack free and is not useful for pressure sensitive adhesive applications. When using SRC18 catalyst with PSA529 adhesive for laminating (bonding) dissimilar materials, follow SRC18 catalyst data sheet (document #CDS5187) precautions carefully.

Bonding Applications

Catalyzed adhesive may be applied with a brush, roller or any suitable coating device. Thinning, if required, may be done with toluene or paint thinner. Both surfaces to be bonded should be thoroughly cleaned with alcohol, the adhesive should be applied to them and allowed to dry either in room temperature or in an elevated temperature. The length of drying time will depend on solvent used, adhesive thickness and temperature it is exposed to. The recommended adhesive thickness is 3 to 4 mils dry. After the solvent is completely evaporated from the adhesive, the surfaces to be bonded should be firmly pressed together and the adhesive should be allowed to cure.

Cure is a function of time and temperature. Room temperature cure at 21° C-25° C (70° F-77° F) will require 3-7 days for the catalyzed adhesive to develop maximum strength. The cure time can be shortened by elevating temperature to a maximum 165° C (329° F). A typical shortened cure cycle is 24 hours at 25° C (77° F) followed by 24 hours at 100° C (212° F). Note: Use adhesive in a well- ventilated area.

Blending Instructions

Typical Formulation	
PSA529	100.0 parts by weight
SRC18	3.3 parts by weight

SRC18 catalyst should be added to the adhesive and stirred well before using (consult Material Safety Data Sheets prior to use).

Store catalyzed adhesive in tightly closed containers and use within 48 hours. Where longer pot life is required, dilute the adhesive mixture to approximately 30% silicone content with toluene or paint thinner. Diluted mixtures are useful up to three months.

Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute the permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

Product Safety, Handling and Storage

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment, if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. SDS are available at www.momentive.com or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

Contact Information

Email

commercial.services@momentive.com

Telephone

Americas

+1 800 295 2392
Toll free*
+704 805 6946
Direct Number

*All American
countries

Latin America

Brazil
+55 11 4534 9650
Direct Number

Mexico
+52 55 2169 7670
Direct Number

EMEAI- Europe, Middle East, Africa & India

Europe
+390510924300
Direct number

India, Middle East & Africa
+ 91 44 71212207
Direct number*

*All Middle Eastern countries,
Africa, India, Pakistan,
Bangladesh, Sri Lanka.

ASIA PACIFIC

China
800 820 0202
Toll free
+86 21 3860 4892
Direct number

Japan
0120-975-400 Toll free
+81 27620 6182
Direct number

Korea
+82 2 6201 4600
Direct number

South East Asia, Australia & New Zealand
+60 3 9206 1543
Direct number*

*South East Asia countries (Malaysia, Singapore, Thailand, Indonesia, Vietnam, Philippines, Cambodia, Myanmar / other countries located in Pacific region).

For literature and technical assistance, visit our website at: www.momentive.com

DISCLAIMER:

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY "SUPPLIER"), ARE SOLD SUBJECT TO SUPPLIER'S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER'S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of Supplier's materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier's products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier's standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

The use of the "™" symbol designates registered or unregistered trademarks of Momentive Performance Materials Inc. or its affiliated companies. Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.



260 Hudson River Road Waterford,
NY 12188 USA
momentive.com

Copyright 2022 Momentive Performance Materials Inc. All rights reserved.