

CLS3060 CLR

Description

CLS3060 CLR is a transparent, self-bonding, two-component silicone rubber for use in liquid injection molding to produce high performance elastomeric parts. CLS3060 CLR is clear, but easily pigmentable. CLS3060 CLR offers a convenient 1:1 mix ratio, high tensile strength, and rapid cure time depending upon part size, configurations and molding temperature.

Key Features and Benefits

- Primer-less adhesion to many substrates
- Maximum adhesion immediately after de-molding
- High clarity for excellent visibility
- High temperature stability
- FDA 21CFR177.2600 (Rubber Articles Intended for Repeated Use) compliant
- Good dielectric and mechanical properties
- Easy pigmentable due to translucent color

Typical Physical Properties

<u>Uncured Properties</u>	
Cure Rate (Monsanto Rheometer MDR 2000 @ 177°C or 350°F; w/ Mylar Sheets)	
Torque, maximum, in/lb	16.3
Peak Rate, in/lb/min	124
T-2, seconds	4.8

T-90, seconds	17.4
Cured Properties	
<u>ASTM slabs cured 15 min @ 177°C (350°F)</u>	
Color	Clear
Specific Gravity	1.12
Hardness, Shore A durometer	59
Tensile Strength, psi	1,600
Elongation, %	500
100% Modulus, psi	310
Tear Die B, ppi	190

Potential Applications

- Sports goggles
- Respiratory masks
- Health care equipment
- Sealing elements & membranes
- Coating metal rolls

Processing Recommendations

Ready-to-use mixtures (of the components A and B) are fed directly to the injection-molding machine from the original containers by means of a metering and mixing unit. The mixture, consisting of the two components in the ratio 1:1, is injected into the heated mold. At mold temperatures of 170 - 230°C, the addition-crosslinking silicone rubber typically vulcanizes, without any dissociation products, within a few seconds. High curing speed and easy demolding can help enable fully automated production of a large number of articles in short cycle times.

Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute the permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

Product Safety, Handling and Storage

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. SDS are available at www.momentive.com or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

Contact Information

Email

commercial.services@momentive.com

Telephone

Americas	Latin America	EMEAI- Europe, Middle East, Africa & India	ASIA PACIFIC
+1 800 295 2392	Brazil	Europe	China
Toll free*	+55 11 4534 9650	+390510924300	800 820 0202
+704 805 6946	Direct Number	Direct number	Toll free
Direct Number			+86 21 3860 4892
			Direct number
*All American countries	Mexico	India, Middle East & Africa	Japan
	+52 55 2169 7670	+ 91 44 71212207	+81 3 5544 3111
	Direct Number	Direct number*	Direct number

***All Middle Eastern Korea**
countries, Africa, India, +82 2 6201 4600

For literature and technical assistance, visit our website at: www.momentive.com

DISCLAIMER:

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY “SUPPLIER”), ARE SOLD SUBJECT TO SUPPLIER’S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER’S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of Supplier’s materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier’s products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier’s standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

***Silopren™ is a trademark of Momentive Performance Materials Inc.**

The use of the "™" symbol designates registered or unregistered trademarks of Momentive Performance Materials Inc. or its affiliated companies. Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.