

## SilForce™ SL6020

### SilForce\* SL6020 Release Coating

#### Description

SL6020-D1 release coating is a reactive polysiloxane copolymer used to cure either SL6000-D1/SL6010-D1 or SL6100-D1/SL6110-D1 release coatings.

#### Key Features and Benefits

- Fast, low temperature cure
- Stable release values
- Reduced oven dusting

#### Typical Physical Properties

PROPERTY	VALUE
Viscosity, cps, 25°C (77° F)	35-40
Specific Gravity, 25°C (77° F)	.98
Density, lbs./gal.	8.17
Flash Point, closed cup, C° (F° )	> 93.3 (> 200)

#### Potential Applications

The SL6000-D1 and SL6100-D1 release coating systems of reactive silicone polymers are intended for use as release coatings on paper and plastic substrates used in the manufacture of pressure sensitive tapes and labels. One- and two-sided constructions are possible.

### **Patent Status**

Standard copy to come

### **Product Safety, Handling and Storage**

The warranty period for SL6020-D1 is 12 months from date of shipment from Momentive Performance Materials if stored in the original unopened container at 25° C (77° F) or below.

Standard copy to come

### **Processing Recommendations**

See Momentive Performance Materials Application Guide on the SL6000-D1 and SL6100-D1 solventless release coating systems.

### **Limitations**

Standard copy to come

### **Specifications**

#### **FDA STATUS**

The SL6000-D1 and SL6100-D1 multi-component release coating systems without a tight release polymer comply with the following FDA regulations:

- 175.320, resinous and polymeric coatings for polyolefin films
- 176.170, components of paper and paperboard in contact with aqueous and fatty foods
- 176.180, components of paper and paperboard in contact with dry foods for use as release surfaces for pressure sensitive adhesives.

Consult these regulations for limitations of use with respect to platinum content, food type and use conditions. Tight release polymers (SL6030, SL6130, SL5030) may only be used as a release coating for pressure sensitive adhesives under regulation 176.180.

### **Availability**

SL6020-D1 may be ordered from Momentive Performance Materials, Waterford, NY,

12188, the Momentive Performance Materials sales office nearest you or an authorized Momentive Performance Materials distributor.

**Contact Information**

Email

[commercial.services@momentive.com](mailto:commercial.services@momentive.com)

**Telephone**

<b>Americas</b>	<b>Latin America</b>	<b>EMEAI- Europe, Middle East, Africa &amp; India</b>	<b>ASIA PACIFIC</b>
+1 800 295 2392 Toll free*	<b>Brazil</b> +55 11 4534 9650 Direct Number	<b>Europe</b> +390510924300 Direct number	<b>China</b> 800 820 0202 Toll free +86 21 3860 4892 Direct number
+704 805 6946 Direct Number	<b>Mexico</b> +52 55 2169 7670 Direct Number	<b>India, Middle East &amp; Africa</b> + 91 44 71212207 Direct number*	<b>Japan</b> +81 3 5544 3111 Direct number
*All American countries		<b>*All Middle Eastern countries, Africa, India,</b>	<b>Korea</b> +82 2 6201 4600

For literature and technical assistance, visit our website at: [www.momentive.com](http://www.momentive.com)

**DISCLAIMER:**

**THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY “SUPPLIER”), ARE SOLD SUBJECT TO SUPPLIER’S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR**

**GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER'S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN.** Each user bears full responsibility for making its own determination as to the suitability of Supplier's materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier's products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier's standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

\*SilForce™ is a trademark of Momentive Performance Materials Inc.

The use of the "™" symbol designates registered or unregistered trademarks of Momentive Performance Materials Inc. or its affiliated companies. Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.