

## SilForce™ SS4192C Release Coating

### Product Description

SilForce SS4192C catalyst is a 50% solution of dibutyl tin diacetate in toluene. When added to a properly formulated coating mixture of Silforce SS4191A, SilForce SS4191B, and SilForce SS4259C diluted to the proper solids content for coating, SS4192C will effect rapid crosslinking of the coated bath at elevated web temperatures.

### System Components:

- SilForce SS4191A silicone gum solution
- SilForce SS4191B methyl hydrogen crosslinker
- SilForce SS4192C tin catalyst
- Silforce SS4259C cure accelerator

### Typical Physical Properties

Property	SS4191A	SS4191B	SS4192C	SS4259C
Haze	30 max.	10 max.	---	30 max.
Appearance	OK	OK	OK	OK
Color Apha	---	15 max.	---	---
Color Gardner	---	---	---	2 max.
Solids %	28-30	---	41-45	48-52
Weight Loss %	---	7%-10%	---	---
Solvent	Toluene	NA	Toluene	Toluene

Typical properties are average data and are not to be used as or to develop specifications.

### Processing Recommendations

To obtain the maximum stability from the SS4191A and SS4191B components when formulating a bath, it is important to follow a specific order of addition along with adequate mixing time to assure a uniform dispersion.

1. Dilute the SS4191A solution to the desired concentration with an appropriate solvent and mix until thoroughly dispersed.
2. Add the SS4191B crosslinker and mix thoroughly. (The objective is to assure a homogeneous dispersion).
3. Add the SS4192C catalyst and mix until uniformly dispersed.
4. Add the SS4259C accelerator and mix until uniformly dispersed. The bath is now ready for use.

### Suggested Formulations

SS4191A and SS4191B components are designed to be used in the ratio of 393 lbs. to 7 lbs. respectively (equivalent ratio of 100 to 1.78). To prepare a 5% solids bath, equivalent formulations are as follows: (In this example, the SS4192C catalyst and the SS4259C accelerator are both at the 2.5% levels based on the amount of SS4191A plus SS4191B components or the amount of SS4191 coating in each formulation).

4 COMPONENT SYSTEM*		3 COMPONENT SYSTEM*	
SS4191A	16.4	SS4191	16.7
Solvent	82.5	Solvent	82.5
SS4191B	0.29 (0.3)	--	--
SS4192C	0.4	SS4192C	0.4
SS4259C	0.4	SS4259C	0.4

\* Number of Silicone (SS) Components only

### SS4191 A + B Blend Chart

The following chart gives percent SS4191A + SS4191B components to be used in formulating various silicone solids coating baths for the SS4191A and SS4191B component system. The levels of SS4192C catalyst and SS4259C accelerator are based on 2.5%. Higher or lower levels can be used depending on application. The order of addition should be the same as shown.

**Mixing Instructions:**

1. Dilute the SS4191A component to the desired silicone solids concentration with your solvent and mix until thoroughly dispersed.
2. Add the SS4191B component and mix until thoroughly dispersed.
3. Add the SS4192C catalyst and mix thoroughly.
4. Add the SS4259 accelerator and mix thoroughly.

<b>% Silicone Solids in Coating Bath</b>	<b>3%</b>	<b>4%</b>	<b>5%</b>	<b>6%</b>	<b>7%</b>	<b>8%</b>
% By weight of SS4191A	10	13.3	16.4	20.0	23.3	26.7
Solvent	89.32	85.78	82.47	78.62	75.11	71.46
SS4191B	0.18	0.24	0.29	0.36	0.41	0.48
SS4192C	0.25	0.34	0.42	0.51	0.59	0.68
SS4259C	0.25	0.34	0.42	0.51	0.59	0.68

**Availability**

Momentive Performance Materials is making SS4191 coating available as a split kit of SS4191A and SS4191B components with the same total weight (400 lbs.) and current pricing as when SS4191 coating is sold as a single material. The split kit is sized such that one 393 lb. drum of SS4191A solution is designed to go with one 7 lb. pail of SS4191B cross-linker. When ordering the new split kit, specify the number of drums of SS4191A component required. Our customer service representatives will code your order for complete shipment. SS4191A and SS4191B components are not sold separately.

**Patent Status**

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute the permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

**Product Safety, Handling and Storage**

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if

necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. SDS are available at [www.momentive.com](http://www.momentive.com) or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

### Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

### Contact Information

Email

[commercial.services@momentive.com](mailto:commercial.services@momentive.com)

### Telephone

<b>Americas</b>	<b>Latin America</b>	<b>EMEAI- Europe, Middle East, Africa &amp; India</b>	<b>ASIA PACIFIC</b>
+1 800 295 2392 Toll free*	<b>Brazil</b> +55 11 4534 9650 Direct Number	<b>Europe</b> +390510924300 Direct number	<b>China</b> 800 820 0202 Toll free +86 21 3860 4892 Direct number
+704 805 6946 Direct Number	<b>Mexico</b> +52 55 2169 7670 Direct Number	<b>India, Middle East &amp; Africa</b> + 91 44 71212207 Direct number*	<b>Japan</b> +81 3 5544 3111 Direct number
*All American countries		<b>*All Middle Eastern countries, Africa, India,</b>	<b>Korea</b> +82 2 6201 4600

For literature and technical assistance, visit our website at: [www.momentive.com](http://www.momentive.com)

**DISCLAIMER:**

**THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY “SUPPLIER”), ARE SOLD SUBJECT TO SUPPLIER’S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER’S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN.** Each user bears full responsibility for making its own determination as to the suitability of Supplier’s materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier’s products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier’s standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

\*SilForce™ is a trademark of Momentive Performance Materials Inc.

The use of the “™” symbol designates registered or unregistered trademarks of Momentive Performance Materials Inc. or its affiliated companies. Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.