

SilForce™ UV9440E Release Coating

SilForce* UV9440E Release Coating

Description

SilForce UV9440E release coating is an additive intended for use in UV curable epoxysilicone release coating formulations. SilForce UV9440E photocures into crosslinked epoxysilicone networks and acts to reduce the 'zippy' character of radiation-cured silicone release, provide for smooth, low coefficient of friction coating character, and premium release of most aggressive pressure sensitive adhesives, particularly at low strip speed. UV9440E reduces the bulk modulus of crosslinked epoxysilicone coatings, which in turn leads to higher release at high peel speed, suitable for high speed roll label converting operations. UV9440E has also been found to assist in release of aggressive mastic, asphaltic, and hydrogel type adhesives. SilForce UV9440E is a linear polydimethylsiloxane with reactive carbinol (alcohol) functionality at the chainstopper positions. SilForce UV9440E can also be used as a curable slip agent in compatible urethane coating formulations.

Key Features and Benefits

- Reduction of Coefficient of Friction of cured epoxysilicone coatings facilitates rewind of thin film silicone liners
- Provides for premium low peel release
- Reduces 'zippy' release performance and initiation spike often observed in cured epoxysilicone release coatings

Typical Physical Properties

Property	Value
Viscosity, 25C	1000 cstk (Ostwald)
Solids*	> 99.5%
Specific Gravity, 25C	0.99
Hydroxyl Equivalent Weight (theoretical)	2500 grams/mole OH

* weight loss, 1 gram, 45 minutes @ 150C

Potential Applications

Substrates

All film and paper substrates compatible with UV9XXX polymers are suitable for UV9440E coatings.

Patent Status

Standard copy to come

Product Safety, Handling and Storage

Standard copy to come

Processing Recommendations

FORMULATION AND APPLICATION

UV9440E may be added to any of the UV9XXX epoxysilicone polymers to alter performance. In general, 2 to 10 parts of UV9440E per 100 parts of total polymer formulation have been found useful to promote premium release and low CoF properties. NOTE: UV9440E cannot be used by itself, but only as an additive. The effect of UV9440E on release performance of easy and tight release coatings is displayed in Figures 1 and 2, respectively. Reduction of CoF by addition of UV9440E is illustrated in Figure 3. UV9440E can be used with various combinations of easy and tight release polymers, the effects of which are depicted in Figure 4. UV9440E provides great latitude in formulation possibilities for users of Momentive Performance Materials

UV9XXX systems. Catalyzed blends of UV9440E plus other epoxysilicone polymers will vary in appearance from very hazy to nearly clear solutions, depending on the precise formulation. UV9380C catalyst may drop out of suspension from hazy coating baths if the bath sets undisturbed for extended periods, necessitating vigorous, thorough remix prior to reuse.

Suggested Formulations

Component	Parts by Weight		
	Formula A	Formula B	Formula C
UV9XXX	98	95	92
UV9440E	2	5	8
UV9380c ^{***}	2	2	2

^{***}Catalyst level recommended for plastic films. For paper substrates, 3 parts of catalyst are recommended.

Bath Preparation

Weigh the required amount(s) of UV9XXX polymer(s) and UV9440E in an inert clean container, mix them thoroughly and add the proper amount of UV9380c catalyst. Mix the bath with a mechanical stirrer for 10 to 15 minutes. Thorough mixing is critical for proper performance. If the bath is left undisturbed for long periods of time, it must be thoroughly re-mixed.

Bath Life

Catalyzed UV9300, UV9315, UV9400, UV9430, UV9425, UV9500/UV9440E baths will be usable for several days if stored in the dark at ambient temperatures. Settling out of catalyst may occur, depending on particular polymers used, so vigorous re-agitation of catalyzed baths is recommended before re-use.

Figure 1




Figure 2




Figure 3





Figure 4

Typical Tight UV System Blend Release;
2% UV9380c, PK Inner, 800 fpm x 2 lamps



** UV9XXX: UV9300, UV9315, UV9400, UV9430, UV9425, UV9500

Limitations

Standard copy to come

Availability

Products may be ordered from Momentive Performance Materials, Waterford, NY 12188, the Momentive Performance Materials' office nearest you or, where appropriate, an authorized Momentive Performance Materials' product distributor.

1 gal	55 gal
8 lbs	400 lbs

Contact Information

Email

commercial.services@momentive.com

Telephone

Americas	Latin America	EMEA- Europe, Middle East, Africa & India	ASIA PACIFIC
+1 800 295 2392	Brazil	Europe	China
Toll free*	+55 11 4534 9650	+390510924300	800 820 0202
+704 805 6946	Direct Number	Direct number	Toll free
Direct Number			+86 21 3860 4892

All American countries	Mexico +52 55 2169 7670 Direct Number	India, Middle East & Africa + 91 44 71212207 Direct number	Direct number Japan +81 3 5544 3111 Direct number
		*All Middle Eastern countries, Africa, India,	Korea +82 2 6201 4600

For literature and technical assistance, visit our website at: www.momentive.com

DISCLAIMER:

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY “SUPPLIER”), ARE SOLD SUBJECT TO SUPPLIER’S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER’S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of Supplier’s materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier’s products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier’s standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement

contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

*SilForce™ is a trademark of Momentive Performance Materials Inc.

The use of the "™" symbol designates registered or unregistered trademarks of Momentive Performance Materials Inc. or its affiliated companies. Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.