

Technical Data Sheet

Electro-Seal 1959

Description

Electro-Seal 1959 is a one-component, low viscosity, oxime cure, solvent type silicone coating that cures on exposure to atmospheric moisture to form an elastomer. The product is suitable for high voltage insulator coating to protect the insulator against insulation deterioration due to deposits of dust, salt particles.

Key Features

- Low viscosity
- Primerless adhesion to many substrates
- Excellent electrical insulation properties
- Excellent arc resistance

Typical Physical Properties

UNCURED PROPERTIES	
Appearance	White, flowable
Viscosity	0.6 Pa's
Tack-free time (23°C)	15 min
Density (23°C)	1.09 g/cm ³
Solid Content (2h @ 150°C)	60%
Solvent	Isoparaffin
CURED PROPERTIES	
Appearance	White elastomer
Density (23C)	1.61 g/cm3
Hardness (Type A)	60
Tensile strength	2.3 MPa (23 kgf/cm2)
Elongation	100%
Volume resistivity	3.0x10 16 cm

Dielectric strength	23 kV/mm
Dielectric constant	3.80 at 100Hz 3.71 at 1kHz 3.60 at 100kHz
Dissipation factor	0.01 at 100Hz 0.01 at 1kHz 0.01 at 100kHz
Arc resistance (ASTM D495)	246

Typical property data value should not be used as specifications

Potential Applications

- High Voltage Insulator coating
- Industrial coating

General Instructions for Use

Apply the product by spraying, brushing or dipping and cure at room temperature.

Handling and Safety

Wear eye protection and protective gloves as required while handling the product.

Adequate ventilation must be maintained in the work place at times.

Storage

Store in a cool dry place out of direct sunlight. Keep out of the reach of children.

Packaging

20kg pail available

Patent Status

本書のいかなる内容も、関連特許が存在しないことを暗示したものではありません。またいか なる特許についても、その権利者による許可なしに、その特許が対象とする発明を実施する ための許可、誘因または推奨を構成することはできません。

Product Safety Handling and Storage

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an aroundthe-clock emergency service for its products. SDS are available at

www.momentive.com or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

Contact Information

Email commercial.services@momentive.com

Telephone

Americas	Latin America	EMEAI- Europe, Middle East, Africa & India	ASIA PACIFIC
+1 800 295 2392	Brazil	Europe	China
Toll free* +704 805 6946	+55 11 4534 9650 Direct Number	+390510924300 Direct number	800 820 0202 Toll free
Direct Number			+86 21 3860 4892
*All American countries	Mexico +52 55 2169 7670 Direct Number	India, Middle East & Africa + 91 44 71212207	Direct number Japan +81 3 5544 3111 Direct number
		Direct number* *All Middle Eastern countries, Africa, India,	Korea +82 2 6201 4600

For literature and technical assistance, visit our website at: www.momentive.com

DISCLAIMER:

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY "SUPPLIER"), ARE SOLD SUBJECT TO SUPPLIER'S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR **GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED** HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER'S STANDARD CONDITIONS OF SALE. SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS **OR SERVICES DESCRIBED HEREIN.** Each user bears full responsibility for making its own determination as to the suitability of Supplier's materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier's products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier's standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

The use of the "TM" symbol designates registered or unregistered trademarks of Momentive Performance Materials Inc. or its affiliated companies. Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.