

HS-4

Weatherstrip Coating

Description

HS-4 weatherstrip coating is a 3-component matte translucent solvent-based silicone coating system that thermally cures to form a resilient silicone film. This system is comprised of a milky base (HS-4A), an adhesion promoter (XC9615 is recommended for both on-line and off-line processing), and a catalyst (YC6831 tin complex or XC94-C6256 tin free). The cured coating can help to provide substrate surfaces such as EPDM rubber with lubricating water repellency and easy release characteristics. HS-4 coating is an excellent candidate to consider for colored dynamic seals such as automotive door seals or other parts where a smooth surface is preferred to impart low friction related noise generation. It can also be considered for numerous non-automotive applications, such as O-rings and other small rubber parts as an assembly aid.

Key Features and Typical Benefits

- Excellent freeze release characteristics
- Low static, dynamic CoF and smooth transition for low noise generation
- Excellent noise reduction properties
- Excellent adhesion to EPDM, TPE and many other rubber formulations
- Fast heat cure process (approx. 1 minute)
- Tin and isocyanate content free formulation (*using XC94-C6256)

Typical Physical Properties

Property	HS-4A Silicone Base	XC9615 Adhesion Promoter	YC6831* Catalyst
Color	Milky White	Colorless	Pale Yellow
Solids Content (%)	27	15	28
Density (@ 23°C)	0.93	0.84	0.99
Viscosity (DIN 4 cup @ 23°C (seconds))	20	13	12
Viscosity (mPas, Brookfield #2 @ 30 rpm)	550		
Solvent	Xylene	IPA	Toluene

Typical properties are average data and are not to be used as or to develop specifications.

Typical Cured Product Properties

Property	Test Method	Value
Coefficient of friction (Static and Dynamic)	DIN 53375	< 0.3
Abrasion Resistance (Crockmeter 900 g load)	Dry Crockmeter	> 500 cycles
Abrasion Resistance (Crockmeter 200 g load)	Dry Crockmeter	> 5000 cycles
Freeze Release	TL 523 45	Pass
Repaintability	TSM 1701 G	Pass
Paint Staining	TSM 1701 G	Pass

Typical properties are average data and are not to be used as or to develop specifications.

Typical Cure Schedule

Complete cure in any specific application is a function of coating thickness, part geometry and the heat transfer characteristics of the substrate to which the coating is being applied.

Although the prepared coating will cure at an ambient temperature, it is not recommended as the adhesion and full abrasion performance may not be realized. An absolute minimum part temperature range of 80-120°C at the point of application is

recommended in order to achieve the full coating performance. Higher substrate temperatures are preferred in order to achieve best adhesion and appearance of the coating.

NOTE: If curing at ambient temperature, the adhesion of coating to the substrate and visual appearance can be compromised.

Part Temperature (actual not oven set point)					
Cure Temperature (°C)	180°C	150°C	100°C	80°C	25°C
Cure Time (at temperature)	1 minute	2 minutes	5 minutes	10 minutes	5 hours min

Sample Coating System¹ Preparation

The following sample formulation is provided as a suggested starting point for spray applications.

Component	Loading by Weight	
HS-4A	100 parts	Supplied as 15 kg pail
XC9615	50 parts	Supplied as 15kg pail
YC6831	7.5 parts	Supplied as 1 kg can
Diluting Solvent (1) (if required)	0 – 400 parts	(2)

1. Compatible solvents include Hexane ,Heptane, White Gasoline, Mineral Spirits and Toluene
2. Further dilution with a solvent may be desired according to the part temperature, type of substrate, required dry film thickness, and application method. The final formulation needs to be established by trials on the end user's production equipment.

¹ Product formulations are included as illustrative examples only. Momentive makes no representation or warranty of any kind with regard to any such formulations, including, without limitation, concerning the efficacy or safety of any product manufactured using such formulations.

General Considerations for Use

It is vitally important to thoroughly mix the HS-4A component to ensure any settled ingredients are well redispersed before use, as settling of the matting agent and friction modifier can occur during storage. Once fully mixed (be sure that no sediment remains in the pail), the base is ready to use. Then add the solvent if required (see above) and finally the catalyst (YC6831 or XC94-C6256). The coating is now ready to use.

CAUTION: The order of addition is important.

The bath should be kept under constant agitation to prevent settling of the active powders and to ensure maximum bath life. For best results, the substrate should be clean and dry and have a minimum temperature of 80°C, as lower application temperatures can adversely affect the adhesion and appearance of the coating. In general, temperatures of 200°C or higher will not affect the coating and may actually lead to productivity gains.

For optimum coating adhesion and performance, ensure all surfaces are clean and dry before applying the coating solution. The substrate temperature should be between 80 – 230°C for on-line application and a minimum of 80°C part temperature at the time of coating for off-line applications, including drum/tumble coating where a suitable drying schedule must be used between each application.

HS-4 weatherstrip coating is recommended to be spray coated.

This coating is typically applied using HVLP spray guns with an aircap diameter < 1.0mm. To avoid blocking of the guns the coating should be filtered through a 200 micron mesh after the coating is prepared. It is good practice to install a further filter between the holding tank and spray guns. Most on-line applications use multiple spray guns to achieve even coverage of the profile during extrusion.

It is important to apply sufficient material to achieve an initial wet look in order to help ensure continuous coverage and good coating adhesion. It is also possible to employ multiple spray heads in tandem to help ensure sufficient coating is applied and no areas are left uncoated during the application process.

Typical bath life is 12 hours in a partially closed container. Continuous slow speed agitation of the coating bath is recommended to reduce the possibility of settling of the matting agents and friction modifiers.

The resulting coating thickness will depend on the application method and the required end-use requirements.

Dry film thicknesses are typically between 6 and 10 microns.

Current Packaging

HS-4	15 liter metal pails
XC9615	15 liter pails 14 kg fill
YC6831	1 kg metal cans

Patent Status

本書のいかなる内容も、関連特許が存在しないことを暗示したものではありません。またいかなる特許についても、その権利者による許可なしに、その特許が対象とする発明を実施するための許可、誘因または推奨を構成することはできません。

Product Safety, Handling and Storage

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. SDS are available at www.momentive.com or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

Contact Information

Email

commercial.services@momentive.com**Telephone**

Americas	Latin America	EMEAI- Europe, Middle East, Africa & India	ASIA PACIFIC
+1 800 295 2392	Brazil	Europe	China
Toll free*	+55 11 4534 9650	+390510924300	800 820 0202
+704 805 6946	Direct Number	Direct number	Toll free
Direct Number			+86 21 3860 4892
			Direct number
*All American countries	Mexico	India, Middle East & Africa	Japan
	+52 55 2169 7670	+ 91 44 71212207	+81 3 5544 3111
	Direct Number	Direct number*	Direct number
		*All Middle Eastern countries, Africa, India,	Korea
			+82 2 6201 4600

For literature and technical assistance, visit our website at: www.momentive.com

DISCLAIMER:

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY "SUPPLIER"), ARE SOLD SUBJECT TO SUPPLIER'S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE.

EXCEPT AS PROVIDED IN SUPPLIER'S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of Supplier's materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier's products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier's standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

The use of the "™" symbol designates registered or unregistered trademarks of Momentive Performance Materials Inc. or its affiliated companies. Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.