


OphthaSil™ 4000 silicone surfactant TDS

OphthaSil* 4000 silicone surfactant

Description

OphthaSil 4000 is a pendant structure silicone block polyether surfactant.



OphthaSil 4000 silicone surfactant may help increase wettability, lubricity or release in contact lens manufacturing.

Key Features and Typical Benefits

- Water Soluble
- Wetting
- Lubricating
- Releasing

Potential Applications

- Contact Lens Processing

Typical Physical Properties

Property	Value
MW (g/mol)	4000
Color GVS ¹	2
Specific Gravity 25/25°C	1.066
Flash Point ² (°C)	74[165°F]
Viscosity @25°C (cSt)	110
Solvent pH @25°C	7
Refractive Index @25°C	1.45
Surface Tension ³ (mN/m)	25.1
Cloud Point ⁴ (°C)	64[147°F]
CMC Weight ⁵ (g/100g)	0.005
Polyether Type	All EO

Typical properties are average data and are not to be used as or to develop specifications.

¹ Gardner Varnish Scale

² Pensky-Martens, Closed Cup, ASTM method D93

³ Surface tension at 25°C on 0.1% (w/w) aqueous solutions either DeNooy Ring or Wihelmy Plate method.

⁴ Cloud Point measured visually on 1% (w/w) aqueous solutions

⁵ Critical Micelle Concentration in water

Availability

OphthaSil 4000 silicone surfactant is currently available in 0.9kg bottles and 18kg pails (typical average weights).

Shelf Life & Storage

The typical shelf life of four years from the date of manufacture of the material will be indicated by the “use before date” on the associated documents when stored in the unopened containers at 43°C or less.

Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute the permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

Product Safety, Handling and Storage

Customers should review the latest Material Safety Data Sheet (MSDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. MSDS are available at www.momentive.com or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

Contact Information

Email

commercial.services@momentive.com

Telephone

Americas	Latin America	EMEAI- Europe, Middle East, Africa & India	ASIA PACIFIC
Brazil	Europe	China	
+1 800 295 2392	+390510924300	800 820 0202	
Toll free*	Direct number	Toll free	
+704 805 6946		+86 21 3860 4892	
Direct Number		Direct number	
Mexico	India, Middle East & Africa	Japan	
+52 55 2169 7670	+ 91 44 71212207	+81 3 5544 3111	
Direct Number	Direct number*	Direct number	
*All American countries	*All Middle Eastern countries, Africa, India,	Korea	

For literature and technical assistance, visit our website at: www.momentive.com

DISCLAIMER:

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY “SUPPLIER”), ARE SOLD SUBJECT TO SUPPLIER’S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER’S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of Supplier’s materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier’s products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier’s standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

* OphthaSil™は Momentive Performance Materials Inc. の商標です。

The use of the “™” symbol designates registered or unregistered trademarks of Momentive Performance Materials Inc. or its affiliated companies. Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.