

YF33-1000

耐熱性ジメチルシリコーンオイル

YF33シリーズは、耐熱性に優れた茶褐色透明のメチル系シリコーンオイルです。

特長

- 開放系での耐熱性に優れています。

用途

- 開放系で使用される油浴、熱媒、防振油など
- 高温でのプラスチック・ゴム潤滑離型用オイル

特性例

項目	YF33-100	YF33-1000	YF33-3000	YF33-1M
外観	茶褐色透明	茶褐色透明	茶褐色透明	茶褐色透明
比重 (25°C)	0.968	0.971	0.973	0.975
粘度 (25°C) mm ² /s	100	1,000	3,000	10,000
加熱減量 (150°C、24h) %	0.3	0.3	0.3	0.3
粘度温度係数*	0.59	0.60	0.60	0.60
流動点 °C	-50以下	-50以下	-40以下	-40以下
耐熱性 (250°C、1000h)	ゲル化せず	ゲル化せず	ゲル化せず	ゲル化せず
耐熱性 (300°C、48h)	ゲル化せず	ゲル化せず	ゲル化せず	ゲル化せず

* 温度粘度係数=1-98.9°Cにおける粘度/37.8°Cにおける粘度


耐熱性(開放系)

試験条件


サンプル量 : 30g

サンプル容器 : 50mlビーカー、直径42mm

粘度変化



重量減少



取扱い上の注意

- 取扱い時には、保護眼鏡および必要に応じて保護手袋を着用してください。
- 換気のよい所で使用してください。

保管

- 直射日光を避け、湿気の少ない屋内冷暗所に保管してください。
- 子供の手の届かない所に保管してください。

荷姿・梱包

- YF33-100 : 1kgポリビン(1ケース10P入り)、15kg石油缶
- YF33-1000 : 1kgポリビン(1ケース10P入り)、15kg石油缶、200kgドラム
- YF33-3000 : 1kgポリビン(1ケース10P入り)、15kg石油缶
- YF33-1M : 1kgポリビン(1ケース10P入り)、15kgペール缶

消防法

- YF33-100 : 非危険物。指定可燃物の可燃性液体類に該当。
- YF33-1000 : 非危険物。指定可燃物の可燃性液体類に該当。
- YF33-3000 : 非危険物。指定可燃物の可燃性液体類に該当。
- YF33-1M : 非危険物。指定可燃物の可燃性液体類に該当。

特許状況

本書のいかなる内容についても、関連特許が存在しないことを暗示したものと解釈してはならず、またいかなる特許についても、その権利者による許可なく、その特許が対象とする発明を実施するための許可、誘因または推奨を構成するものと解釈してはなりません。

製品の安全性、取り扱いおよび保管

製品の安全情報、安全な取扱手順、個人用保護具(必要な場合)、緊急サービスの連絡先情報、および安全な保管に必要な条件については、最新の安全データシート(SDS)および製品ラベルで確認してください。SDSは www.momentive.com で入手するか、あるいは MPM の担当者にご依頼ください。他の素材を MPM 製品(例:プライマー)と合わせて使用する際は、追加的な注意が必要になる場合があります。他の素材の製造者による安全情報を読み、それに従ってください。

制限

お客様はモメンティブ・パフォーマンス・マテリアルズ製品を評価し、特定の用途に対する使用適合性をご自身で判断する必要があります。

Contact Information

Email

commercial.services@momentive.com

Telephone

Americas	Latin America	EMEA- Europe, Middle East, Africa & India	ASIA PACIFIC
+1 800 295 2392 Toll free* +704 805 6946 Direct Number	Brazil +55 11 4534 9650 Direct Number	Europe +390510924300 Direct number	China 800 820 0202 Toll free +86 21 3860 4892 Direct number
All American countries	Mexico +52 55 2169 7670 Direct Number	India, Middle East & Africa + 91 44 71212207 Direct number	Japan +81 3 5544 3111 Direct number
		*All Middle Eastern countries, Africa, India,	Korea +82 2 6201 4600

For literature and technical assistance, visit our website at: www.momentive.com

DISCLAIMER:

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY “SUPPLIER”), ARE SOLD SUBJECT TO SUPPLIER’S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED

HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER'S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of Supplier's materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier's products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier's standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

The use of the "™" symbol designates registered or unregistered trademarks of Momentive Performance Materials Inc. or its affiliated companies. Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.