

## FSE 7340

### FSE 7340

#### Description

**FSE 7340** is a fluorosilicone rubber, designed for calendaring and moulding for a variety of solvent resistant applications. These products may be used with different peroxides and fillers to develop wide-ranging property profiles. This high tear resistant material is successfully used in a variety of automotive and aerospace applications, where a combination of excellent fluid-resistance with good overall mechanical properties, low-temperature performance and high tear resistance is required.

#### Key Features and Benefits

- Excellent handling
- Blendable
- Easy pigmentable
- Broad fluid resistance
- High tear resistance
- Low temperature flexibility
- Suitable for high temperature applications
- Constant physical properties over wide temperature range

#### Typical Physical Properties

<u>Typical Properties of the Uncured Base Compound:</u>			
Appearance			Pale yellow
Density	DIN 53 479 A	g/cm <sup>3</sup>	1.43
<u>Typical Properties of the Vulcanized Rubber:</u>			

100 phr FSE 7340 with 1.5 phr 2,5 Dimethyl-2,5 Di(t-butyl peroxy)Hexane (50%)  
 Vulcanization conditions: 15 min. @ 177°C post cured: 4h @ 204°C in hot air

Hardness	DIN 53 505*	Shore A	42
Tensile strength	DIN 53 504 S2*	N/mm <sup>2</sup>	11.2
Elongation at break	DIN 53 504 S2*	%	500
Tear strength	ASTM D 624 die B	N/mm	42
Compression set (22 h @ 177°C)	DIN 53 517*	%	8

\*The quoted test methods are corresponding to ASTM standards.

### Processing Recommendations

Various organic peroxides will vulcanize **FSE 7340** fluorosilicone compounds. Fabricators should make their selection of curing agents on the basis of method of fabrication, desired properties, and safety considerations. They are mixed into the rubber, if necessary together with **Silopren® HV Additives**. The optimum cure cycle will depend on the method of processing used and the physical dimensions of the vulcanized product. Specific applications will require the use of air oven post cures.

### Packaging

**FSE 7340** is available in 22,7 kg and 454 kg boxes.

### Patent Status

여기에 포함된 어떠한 내용도 관련 특허가 없음을 의미하거나 특허 소유자의 허가 없이 특허에서 다루는 발명을 실행하기 위한 허가, 유도 또는 권고를 구성하는 것으로 해석되어서는 안됩니다.

### Product Safety, Handling and Storage

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. SDS are available at [www.momentive.com](http://www.momentive.com) or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information

provided by the manufacturer of such other materials.

**Limitations**

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

**Contact Information**

Email

[commercial.services@momentive.com](mailto:commercial.services@momentive.com)

**Telephone**

<b>Americas</b>	<b>Latin America</b>	<b>EMEAI- Europe, Middle East, Africa &amp; India</b>	<b>ASIA PACIFIC</b>
+1 800 295 2392 Toll free* +704 805 6946 Direct Number	<b>Brazil</b> +55 11 4534 9650 Direct Number	<b>Europe</b> +390510924300 Direct number	<b>China</b> 800 820 0202 Toll free +86 21 3860 4892 Direct number
*All American countries	<b>Mexico</b> +52 55 2169 7670 Direct Number	<b>India, Middle East &amp; Africa</b> + 91 44 71212207 Direct number*	<b>Japan</b> +81 3 5544 3111 Direct number
		<b>*All Middle Eastern countries, Africa, India,</b>	<b>Korea</b> +82 2 6201 4600

For literature and technical assistance, visit our website at: [www.momentive.com](http://www.momentive.com)

**DISCLAIMER:**

**THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY “SUPPLIER”), ARE SOLD SUBJECT TO SUPPLIER’S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR**

**OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER'S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN.** Each user bears full responsibility for making its own determination as to the suitability of Supplier's materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier's products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier's standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

The use of the "™" symbol designates registered or unregistered trademarks of Momentive Performance Materials Inc. or its affiliated companies. Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.