

Bulk density	0.35	0.36	0.43	0.17	0.46	0.25	0.46
Specific surface area m ² /g	15-35	10-30	10-30	20-45	18	70	20-30
Linseed Oil absorption Rate mL/100g	75	62	58	84	50	95	60

HEAT STABILITY

The following table shows the percentage of weight loss of Tospearl 120 and Tospearl 240 after heating to 350°C and 900°C.

	Tospearl 120	Tospearl 240
Weight loss % @ 350°C	2-3	2-3
Weight loss % @ 900°C	10-12	10-12

Note: Rate of temperature increase = 5°C/min

Potential Applications

Antiblocking Agent in Plastics Films: Tospearl series resins can decrease the contact between film layers, preventing them from sticking together. The silicone also improves clarity in the films while requiring lower usage levels than other antiblocks such as silica. Lubricity and spherical shape of these resins are said to improve extrusion output rates and slip characteristics of the film. The variety of particle sizes available makes these resins suitable for a variety of film thicknesses.

Paints and Inks: Tospearl series resins may be used in paints and inks to improve moisture resistance, to control viscosity, and for clarification of color tone and gloss control.

Toner Additive: Tospearl series resins may be used in copy machine and laser printer toners to control fluidity and to prevent static electricity.

Patent Status

여기에 포함된 어떠한 내용도 관련 특허가 없음을 의미하거나 특허 소유자의 허가 없이 특허에서 다루는 발명을 실행하기 위한 허가, 유도 또는 권고를 구성하는 것으로 해석되어서는 안 됩니다.

Product Safety, Handling and Storage

The warranty period is 12 months from date of shipment from Momentive Performance Materials if stored in the original unopened container at 27°C (80°F).

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. SDS are available at www.momentive.com or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

Specifications

FDA STATUS

Tospearl series resins comply with 21CFR 177.1520 (b) as optional adjuvant substances required in the production of olefin polymers. These resins may be used only as lubricants or anti-blocking agents at a level up to 0.5% in olefin polymers complying with this regulation.

Availability

Tospearl series of silicone resins may be ordered from Momentive Performance Materials, Waterford, NY, the Momentive Performance Materials sales office nearest you or an authorized Momentive Performance Materials' product distributor. Tospearl series silicone resins are available in the following container sizes:

	Metric	US
Tospearl 130	1K, 10K	2.2lb., 22.0lb.
Tospearl 145	1K, 10K	2.2lb., 22.0lb.
Tospearl 240	1K, 10K	2.2lb., 22.0lb.
Tospearl 120	1K, 10K	2.2lb., 22.0lb.
Tospearl 3120	1K, 10K	2.2lb., 22.0lb.
Tospearl 105	1K, 10K	2.2lb., 22.0lb.
Tospearl 2000B	1K, 10K	2.2lb., 22.0lb.

Contact Information

Email

commercial.services@momentive.com

Telephone

Americas	Latin America	EEMEA- Europe, Middle East, Africa & India	ASIA PACIFIC
+1 800 295 2392 Toll free*	Brazil +55 11 4534 9650 Direct Number	Europe +390510924300 Direct number	China 800 820 0202 Toll free +86 21 3860 4892 Direct number
+704 805 6946 Direct Number	Mexico +52 55 2169 7670 Direct Number	India, Middle East & Africa + 91 44 71212207 Direct number*	Japan +81 3 5544 3111 Direct number
*All American countries		*All Middle Eastern countries, Africa, India,	Korea +82 2 6201 4600

For literature and technical assistance, visit our website at: www.momentive.com

The use of the “™” symbol designates registered or unregistered trademarks of Momentive Performance Materials Inc. or its affiliated companies. Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.