

**Technical Data Sheet** 

# **TSE3051**

# Description

TSE3051 is a transparent, one-component, low viscosity silicone potting gel designed for electronic potting applications. This product cures with heat in a short period of time to a soft, tacky gel used to protect delicate electronic assemblies from humidity, dirt, and vibration.

# Key Features and Typical Benefits

- Easy to use one component, no mixing required, long pot life
- Low viscosity pours easily, penetrates complex assemblies
- Heat accelerated cure
- Fast heat cure system
- Soft, tacky, sticky gel
- Absorbs shock and protects delicate mechanical components from vibration

### **Typical Physical Properties**

Property_	<u>Unit</u>	Value		
UNCURED PROPERTIES				
Appearance		Transparent		
Viscosity (23 °C)	Pa•s	0.7		
Specific Gravity (23 °C)	g/cm <sup>3</sup>	0.97		
CURED PROPERTIES (2 hrs at 125 °C)				
Appearance		Gel		
Penetration		85		
Volume Resistivity	Ω•cm	1.0 x 10 <sup>15</sup>		
Storage shear modulus (G') (1)	Pa (dyn/cm²)	450 (4500)		

Loss shear modulus (G") <sup>(1)</sup>	Pa (dyn/cm²)	170 (1700)
Loss tangent (G"/G')		0.4
Poisson's ratio		0.5
Specific heat	J/(g·K)	1.51
Thermal Conductivity	W/m·K	0.17
Dielectric Strength	kV/mm	18
Dielectric Constant (60 Hz)		2.8
Dissaption Factor (60Hz)		0.001
Water Absorption <sup>(2)</sup>	%	0.05
Moisture permeability <sup>(3)</sup>	g/m²•24 hrs.	110

Typical physical properties are average data and should not be used as or to develop product specifications.

(1) 10rad/s at 25 °C (2) ASTM D 570

<sup>(3)</sup> JIS Z 0208

# **Typical Applications**

- Electrical and electronic potting such as hybrid IC insulation potting
- Power devices such as power module potting
- Mechanical cushioning and vibration dampening material for delicate assemblies

# Processing Recommendations

### Compatibility

TSE3051 silicone potting gel will cure in contact with most clean, dry surfaces. However, certain materials, such as butyl and chlorinated rubber, sulfur-containing materials, amines, and certain metal soap cured RTV silicone rubber compounds can cause cure inhibition. Cure inhibition is characterized by a greasy appearance of the TSE3051 silicone potting gel at the interface between the gel and the substrate to be bonded. It is recommended that a sample patch test should be performed with the TSE3051 silicone potting gel to determine substrate compatibility.

### **Surface Preparation**

The adhesive performance of any polymer system is highly dependent upon proper

surface preparation. In order to maximize the adhesion of TSE3051 silicone potting gel and minimize the potential for cure inhibition, all parts should be as clean and dry as possible prior to the application of the gel.

#### Curing

TSE3051 silicone potting gel requires the use of elevated temperatures in order to achieve full cure. Typical cure times and temperatures are as follows:

100 °C	4 hours
125 °C	2 hours
150 °C	1 hours

Note: Test data. Actual results may vary.

The actual cure time is affected by such things as cross-sectional thickness of the TSE3051 silicone potting gel, heat capacity of the overall assembly and efficiency and type of oven used (i.e. convection, infrared).

#### **Patent Status**

여기에 포함된 어떠한 내용도 관련 특허가 없음을 의미하거나 특허 소유자의 허가 없이 특허에서 다루는 발명을 실행하기 위한 허가, 유도 또는 권고를 구성하는 것으로 해석되 어서는 안됩니다.

#### Product Safety, Handling and Storage

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an aroundthe-clock emergency service for its products. SDS are available at www.momentive.com or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

#### Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

# Contact Information

Email commercial.services@momentive.com

#### Telephone

Americas	Latin America	EMEAI- Europe, Middle East, Africa & India	ASIA PACIFIC
+1 800 295 2392	Brazil	Europe	China
Toll free*	+55 11 4534 9650	+390510924300	800 820 0202
+704 805 6946	Direct Number	Direct number	Toll free
Direct Number			+86 21 3860 4892
			Direct number
*All American	Mexico	India, Middle East &	Japan
countries	+52 55 2169 7670	Africa	+81 3 5544 3111
	Direct Number	+ 91 44 71212207	Direct number
		Direct number*	
		*All Middle Eastern	Korea
		countries, Africa, India,	+82 2 6201 4600

For literature and technical assistance, visit our website at: www.momentive.com

#### **DISCLAIMER:**

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY "SUPPLIER"), ARE SOLD SUBJECT TO SUPPLIER'S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR **GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED** HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER'S STANDARD CONDITIONS OF SALE. SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS **OR SERVICES DESCRIBED HEREIN.** Each user bears full responsibility for making its own determination as to the suitability of Supplier's materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier's products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier's standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

The use of the "TM" symbol designates registered or unregistered trademarks of Momentive Performance Materials Inc. or its affiliated companies. Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.