

SiLFORT™ UVHC7300 Clear Coat

Description

SiLFORT™ UVHC7300 clear coat is a non-weatherable, solvent-based, UV radiation cured coating, used to protect plastic substrates from scratching and chemical substances. With its high pencil hardness, steel wool and mar-resistance, it offers exceptional protection to sheet or film materials, particularly those made from PC, PET, TAC or PMMA. SiLFORT UVHC7300 clear coat can be cured at low UV-cure dosage and typically exhibits low “curl” after cure.

Key Features and Typical Benefits

- Excellent abrasion, scratch and mar resistance
- Low “curl” after cure
- Low cure shrinkage
- Solvent/chemical resistance
- Easy-to-clean surface
- Optical clarity
- Easy processing
- Low UV-cure dosage

Potential Applications

- Sheet and film coating
- Automotive interior components

Typical Physical Properties ⁽¹⁾

Property	Unit	Typical Value
Physical form	-	Liquid
Appearance	-	Clear, slightly yellow
Solids content	% by weight	Approx. 60
Dynamic viscosity (@ 25°C)	mPa*s	Approx. 40
Density (@ 25°C)	g/cm ³	Approx. 1.16
Shelf life ⁽²⁾	Months	24

(1) Typical properties are average data and are not to be used as or to develop specifications.

(2) From date of manufacture

General Considerations for Use

Application method	Spray, flow, dip, roller coating, digital printing
Reducing solvents	1-Methoxy-2-propanol (CAS#107-98-2) Methyl-isobutyl-ketone (CAS#108-10-1) 2-Butanol (CAS#78-92-2) 2-Propanol (CAS#67-63-0) ⁽³⁾
Relative humidity (application and ambient flash off)	Max. 65%
Room temperature flash off	20 – 30°C for 1 – 3 minutes
Pre-heating	1 - 3 minutes to reach 60 - 90°C ^{(4), (5)}
Intermediate cool down	Optional
Typical UV-cure	0.5 – 1.5 J/cm ² UV-A ^{(6), (7)}
Recommended hardcoat thickness	> 5 µm ^{(8), (9)}
Recommended thickness of interpenetrating layer	> 1 µm (only required for Polycarbonate) ^{(8), (9)}

(3) Other suitable solvents may be considered

(4) Part surface temperature. Longer pre-heating times may be required when using convection heating instead of IR-heating

(5) Higher heat resistant polymers may require higher pre-heat temperatures

(6) Use of un-doped, medium pressure mercury arc lamps or microwave powered Hg lamps with > 80 W/cm power is recommended. Typical UV- irradiance is 0.2 to 0.6 W/cm² UV-A irradiance

(7) EIT Inc. Power Puck II Device

(8) Interferometrical measurement. FFT-methodology. Refractive Index n = 1.5

(9) Depending on specific customer test requirements

For best results in applying clear coat, filter the coating solution by combining a 5 µm

pre-filter, followed by a 1 µm absolute gel filter.

To help ensure adequate UV-cure, work with the UV-lamp supplier to select UV-reflectors that are appropriate for the parts to be treated. Do not expose liquid product to any source of visible white light prior to UV-cure. To avoid exposure when white light is present, do not use semi-transparent pipework.

Packaging

Currently available in:

20 kg Steel drum with inner surface epoxy-phenolic resin coating

Patent Status

여기에 포함된 어떠한 내용도 관련 특허가 없음을 의미하거나 특허 소유자의 허가 없이 특허에서 다루는 발명을 실행하기 위한 허가, 유도 또는 권고를 구성하는 것으로 해석되어서는 안됩니다.

Product Safety, Handling and Storage

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. SDS are available at www.momentive.com or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

Contact Information

Email

commercial.services@momentive.com

Telephone

Americas	Latin America	EMEAI- Europe, Middle East, Africa & India	ASIA PACIFIC
+1 800 295 2392 Toll free*	Brazil +55 11 4534 9650 Direct Number	Europe +390510924300 Direct number	China 800 820 0202 Toll free +86 21 3860 4892 Direct number
All American countries	Mexico +52 55 2169 7670 Direct Number	India, Middle East & Africa + 91 44 71212207 Direct number *All Middle Eastern countries, Africa, India,	Japan +81 3 5544 3111 Direct number Korea +82 2 6201 4600

For literature and technical assistance, visit our website at: www.momentive.com

DISCLAIMER:

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY “SUPPLIER”), ARE SOLD SUBJECT TO SUPPLIER’S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE.

EXCEPT AS PROVIDED IN SUPPLIER'S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of Supplier's materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier's products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier's standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

*SiiFORTH™는 Momentive Performance Materials Inc.의 상표입니다.

The use of the "™" symbol designates registered or unregistered trademarks of Momentive Performance Materials Inc. or its affiliated companies. Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.