

## SilGrip™ PSA6573A Pressure Sensitive Adhesive

### SilGrip\* PSA6573A Pressure Sensitive Adhesive

#### Description

PS6573A silicone pressure sensitive adhesive is a toluene solution of polysiloxane gum and resin. It is supplied at 60 percent silicone solids and may be further diluted with aromatic, aliphatic or chlorinated solvents. PSA6573A may be blended with SR545 resin dispersion or with other methyl based silicone pressure sensitive adhesives to obtain specific performance properties. PSA6573A adhesive has higher shear and creep resistance than standard silicone pressure sensitive adhesives and displays excellent adhesion to low surface energy materials such as polyethylene, polypropylene, MYLAR® polyester, KAPTON® polyimide and a variety of fluoropolymers such as ACLAR® fluorohalocarbon, TEFLON® tetrafluoroethylene, and FEP.

PSA6573A adhesive may be an excellent choice for laminating films and foils, in bonding applications as a replacement for mechanical fasteners and as a base for printing inks.

#### Key Features and Benefits

- Wide temperature range performance, maintains good shear and tack properties at intermittent temperatures up to 500 °F
- Adhesion to a wide variety of surfaces including low energy surfaces (silicones, fluoropolymers, polyolefines)
- Resistance to moisture, weathering (ozone, sunlight), chemical (acids, alkalis, oils) and biological (fungus) attack
- Excellent laminate shear forces despite differing coefficients of thermal expansion

- Low tack at room temperature, becomes aggressively pressure sensitive at 93°C (200°F)
- Excellent peel and shear strength

### Typical Physical Properties

Property	Value
Silicone Solids, %	60
Viscosity @ 25°C (77°F), cps Brookfield RVF, #6 Spindle @ 20 rpm	19,000
Flash Point, ASTM D-93, °C(°F)	4 (40)
Solvent	Toluene

### TYPICAL CURED ADHESIVE PROPERTIES

Property	Value
Peel Strength <sup>(1)</sup> , grams/inch	2200
Creep Resistance <sup>(2)</sup> , minutes	165
Tack <sup>(3)</sup> , ASTM D2979, grams/cm <sup>2</sup>	200 max.

(1) 2 mil polyester film, stainless steel, 2 mil dry adhesive build, 180° angle, 12 inch/minute @24°C (75°F)

(2) 2 mil polyester film, stainless steel, 2 mil dry adhesive thickness, 1/2 inch<sup>2</sup> overlap, 500grams load, 70°C(158°F)

(3) Probe Tack Tester, 200 grams load

### Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute the permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

### Product Safety, Handling and Storage

The warranty period is 6 months from date of shipment from Momentive Performance

Materials if stored in the original unopened container at 25°C (77°F) or below.

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. SDS are available at [www.momentive.com](http://www.momentive.com) or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

### **Processing Recommendations**

PSA6573A silicone adhesive is supplied at a viscosity suitable for conventional coating equipment. If necessary, it may be thinned with toluene, xylene or other compatible solvents. After the adhesive is applied to the substrate, it is exposed to a two step process: solvent removal and curing.

### **Processing of PSA6573A Catalyzed with Benzoyl Peroxide**

#### **Solvent Removal**

To achieve optimum adhesive properties, it is essential to optimize the drying step of the process in order to assure that the solvent is removed from the adhesive film before the curing step of the process starts. Improper drying will result in residual solvent entrapment within the adhesive. If the adhesive is then exposed to temperatures higher than 93.5 ° C (200 ° F), decomposing peroxide catalyst can cause crosslinking reaction between solvent and adhesive through methyl groups on siloxane chains and on solvent molecules and adversely affect the properties of the adhesive. Typical temperature range for the drying step of the process is 83 ° C (180 ° F) to 90 ° C (194 ° F). A typical drying cycle is 2 minutes at 90 ° C (194 ° F).

#### **Curing Process**

Once the solvent is removed from the adhesive film, the peroxide cure should be initiated by exposure to heat. A typical curing cycle is 2 minutes at 165 ° C (329 ° F). Longer exposure time and higher temperature, up to 204 ° C (400 ° F), can be used without adverse effects. The exact conditions required to achieve a complete cure will depend on oven length and efficiency, peroxide type and type of substrate used, and should be established during experimental trials on the machine.

## **Catalysts**

High purity, 98% benzoyl peroxide <sup>(4)</sup> in the quantity of 1 to 3% based on silicone solids, has been found to give the most consistent results in curing of silicone pressure sensitive adhesives. In applications requiring low temperature cure, 2,4-dichlorobenzoyl peroxide, which is activated at 132 ° C (270 ° F), can be used. It should be noted that 2,4-dichlorobenzoyl peroxide may generate polychlorinated biphenyls during the curing process.

The peroxide should be dispersed in solvent before it is mixed with the adhesive. Thorough mixing of the peroxide and adhesive to achieve homogeneous dispersion is essential for consistency of finished product.

(4) Available from: Elf Atochem North America, Inc.

ACLAR is a Registered Trademark of Allied Chemical Corporation

KAPTON is a Registered Trademark of DuPont

MYLAR is a Registered Trademark of DuPont

SILGRIP is a Registered Trademark of Momentive Performance Materials

TEFLON is a Registered Trademark of DuPont

## **Limitations**

Customers must evaluate Momentive Performance Materials products and make their

own determination as to fitness of use in their particular applications.

### Contact Information

Email

[commercial.services@momentive.com](mailto:commercial.services@momentive.com)

### Telephone

<b>Americas</b>	<b>Latin America</b>	<b>EMEAI- Europe, Middle East, Africa &amp; India</b>	<b>ASIA PACIFIC</b>
+1 800 295 2392 Toll free*	<b>Brazil</b> +55 11 4534 9650 Direct Number	<b>Europe</b> +390510924300 Direct number	<b>China</b> 800 820 0202 Toll free +86 21 3860 4892 Direct number
+704 805 6946 Direct Number	<b>Mexico</b> +52 55 2169 7670 Direct Number	<b>India, Middle East &amp; Africa</b> + 91 44 71212207 Direct number*	<b>Japan</b> +81 3 5544 3111 Direct number
*All American countries		<b>*All Middle Eastern countries, Africa, India,</b>	<b>Korea</b> +82 2 6201 4600

For literature and technical assistance, visit our website at: [www.momentive.com](http://www.momentive.com)

### DISCLAIMER:

**THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY “SUPPLIER”), ARE SOLD SUBJECT TO SUPPLIER’S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED**

**HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER'S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN.** Each user bears full responsibility for making its own determination as to the suitability of Supplier's materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier's products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier's standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

\*SilGrip™ é uma marca registrada da Momentive Performance Materials Inc.

The use of the "™" symbol designates registered or unregistered trademarks of Momentive Performance Materials Inc. or its affiliated companies. Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.