

Tospearl™ 240

Tospearl* 240

Description

The Tospearl series, Tospearl 120, Tospearl 130, Tospearl 105, Tospearl 240, and Tospearl 3120 are micro-fine silicone resins. These resins are available in a variety of sizes from 0.5 to 12.0 microns for use in different applications. Particle size is finely controlled for optimum consistency.

Key Features and Benefits

- Excellent water repellency, lubricity, and heat resistance
- Insoluble in organic solvents
- No melting by heat up to 900°C
- Minimum coagulation
- Excellent dispersibility

Typical Physical Properties

Appearance	Tospearl 120	Tospearl 130	Tospearl 145	Tospearl 240	Tospearl 3120	Tospearl 105	Tospearl 2000B
Average particle size (µm)	2	3	4.5	4	12.0	0.5	4.8
Water Content (105°C, 60min)	2% or less	2% or less	2% or less	2% or less	2% or less	5% or less	5% or less
pH*	6-8.5	6-8.5	6-8.5	6-8.5	7.5	7.5	6-8.5
Specific gravity (25°C)	1.32	1.32	1.32	1.32	1.32	1.32	1.43

Bulk density	0.35	0.36	0.43	0.17	0.46	0.25	0.46
Specific surface area m ² /g	15-35	10-30	10-30	20-45	18	70	20-30
Linseed Oil absorption Rate mL/100g	75	62	58	84	50	95	60

HEAT STABILITY

The following table shows the percentage of weight loss of Tospearl 120 and Tospearl 240 after heating to 350°C and 900°C.

	Tospearl 120	Tospearl 240
Weight loss % @ 350°C	2-3	2-3
Weight loss % @ 900°C	10-12	10-12

Note: Rate of temperature increase = 5°C/min

Potential Applications

Antiblocking Agent in Plastics Films: Tospearl series resins can decrease the contact between film layers, preventing them from sticking together. The silicone also improves clarity in the films while requiring lower usage levels than other antiblocks such as silica. Lubricity and spherical shape of these resins are said to improve extrusion output rates and slip characteristics of the film. The variety of particle sizes available makes these resins suitable for a variety of film thicknesses.

Paints and Inks: Tospearl series resins may be used in paints and inks to improve moisture resistance, to control viscosity, and for clarification of color tone and gloss control.

Toner Additive: Tospearl series resins may be used in copy machine and laser printer toners to control fluidity and to prevent static electricity.

Patent Status

Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute the permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

Product Safety, Handling and Storage

The warranty period is 12 months from date of shipment from Momentive Performance Materials if stored in the original unopened container at 27°C (80°F).

Customers should review the latest Safety Data Sheet (SDS) and label for product safety information, safe handling instructions, personal protective equipment if necessary, emergency service contact information, and any special storage conditions required for safety. Momentive Performance Materials (MPM) maintains an around-the-clock emergency service for its products. SDS are available at www.momentive.com or, upon request, from any MPM representative. For product storage and handling procedures to maintain the product quality within our stated specifications, please review Certificates of Analysis, which are available in the Order Center. Use of other materials in conjunction with MPM products (for example, primers) may require additional precautions. Please review and follow the safety information provided by the manufacturer of such other materials.

Limitations

Customers must evaluate Momentive Performance Materials products and make their own determination as to fitness of use in their particular applications.

Specifications

FDA STATUS

Tospearl series resins comply with 21CFR 177.1520 (b) as optional adjuvant substances required in the production of olefin polymers. These resins may be used only as lubricants or anti-blocking agents at a level up to 0.5% in olefin polymers complying with this regulation.

Availability

Tospearl series of silicone resins may be ordered from Momentive Performance Materials, Waterford, NY, the Momentive Performance Materials sales office nearest you or an authorized Momentive Performance Materials' product distributor. Tospearl series silicone resins are available in the following container sizes:

	Metric	US
Tospearl 130	1K, 10K	2.2lb., 22.0lb.
Tospearl 145	1K, 10K	2.2lb., 22.0lb.
Tospearl 240	1K, 10K	2.2lb., 22.0lb.
Tospearl 120	1K, 10K	2.2lb., 22.0lb.
Tospearl 3120	1K, 10K	2.2lb., 22.0lb.
Tospearl 105	1K, 10K	2.2lb., 22.0lb.
Tospearl 2000B	1K, 10K	2.2lb., 22.0lb.

Contact Information

Email

commercial.services@momentive.com

Telephone

Americas	Latin America	EMEAI- Europe, Middle East, Africa & India	ASIA PACIFIC
+1 800 295 2392 Toll free*	Brazil +55 11 4534 9650 Direct Number	Europe +390510924300 Direct number	China 800 820 0202 Toll free +86 21 3860 4892 Direct number
+704 805 6946 Direct Number	Mexico +52 55 2169 7670 Direct Number	India, Middle East & Africa + 91 44 71212207 Direct number*	Japan +81 3 5544 3111 Direct number
*All American countries		*All Middle Eastern countries, Africa, India,	Korea +82 2 6201 4600

For literature and technical assistance, visit our website at: www.momentive.com

DISCLAIMER:

THE MATERIALS, PRODUCTS AND SERVICES OF MOMENTIVE PERFORMANCE MATERIALS INC. AND ITS SUBSIDIARIES AND AFFILIATES (COLLECTIVELY “SUPPLIER”), ARE SOLD SUBJECT TO SUPPLIER’S STANDARD CONDITIONS OF SALE, WHICH ARE INCLUDED IN THE APPLICABLE DISTRIBUTOR OR OTHER SALES AGREEMENT, PRINTED ON THE BACK OF ORDER ACKNOWLEDGMENTS AND INVOICES, AND AVAILABLE UPON REQUEST. ALTHOUGH ANY INFORMATION, RECOMMENDATIONS, OR ADVICE CONTAINED HEREIN IS GIVEN IN GOOD FAITH, SUPPLIER MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, (i) THAT THE RESULTS DESCRIBED HEREIN WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN INCORPORATING ITS PRODUCTS, MATERIALS, SERVICES, RECOMMENDATIONS OR ADVICE. EXCEPT AS PROVIDED IN SUPPLIER’S STANDARD CONDITIONS OF SALE, SUPPLIER AND ITS REPRESENTATIVES SHALL IN NO EVENT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS OR SERVICES DESCRIBED HEREIN. Each user bears full responsibility for making its own determination as to the suitability of Supplier’s materials, services, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Supplier’s products, materials, or services will be safe and suitable for use under end-use conditions. Nothing in this or any other document, nor any oral recommendation or advice, shall be deemed to alter, vary, supersede, or waive any provision of Supplier’s standard Conditions of Sale or this Disclaimer, unless any such modification is specifically agreed to in a writing signed by Supplier. No statement contained herein concerning a possible or suggested use of any material, product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right of Supplier covering such use or design, or as a recommendation for the use of such material, product, service or design in the infringement of any patent or other intellectual property right.

*Tospearl™ é uma marca registrada da Momentive Performance Materials Inc.

The use of the “™” symbol designates registered or unregistered trademarks of Momentive Performance Materials Inc. or its affiliated companies. Momentive and the Momentive logo are trademarks of Momentive Performance Materials Inc.